

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



No

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C09C 3/10, 1/56		A1	(11) International Publication Number: WO 00/05313 (43) International Publication Date: 3 February 2000 (03.02.00)
(21) International Application Number: PCT/GB99/02378 (22) International Filing Date: 22 July 1999 (22.07.99) (30) Priority Data: 09/122,164 24 July 1998 (24.07.98) US (71) Applicant: THE GENERAL ELECTRIC COMPANY, P.L.C. [GB/GB]; One Bruton Street, London W1X 8AQ (GB). (72) Inventor: KWAN, Wing, Sum, Vincent; 326 Inverrary Lane, Deerfield, IL 60015 (US). (74) Agent: MCGOWAN, Nigel, George; GEC Patent Dept., Waterhouse Lane, Chelmsford, Essex CM1 2QX (GB).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: HYDROPHOBIC MODIFICATION OF CHARGEABLE PIGMENT PARTICLES			
(57) Abstract <p>The present invention provides a method for making a non-polar suspension of chargeable pigment particles. A suspension of pigment particles is formed in a non-polar solvent, wherein the pigment particles are inherently ionic or are chargeable, and possess surface anchoring groups on the surface of the pigment particles. The pigment particles are contacted with a polymeric resin comprising a hydrophobic region that is soluble or solvatable in the non-polar solvent and a reactive group that reacts with the surface-anchoring groups on the surface of the pigment particle. The resultant coated pigment particles are stable in non-polar suspensions. In certain embodiments of the present invention, a covalent bond is formed between the pigment and the surface modifying polymer.</p>			

102 (b)

*Polymer
modified
Surface*

all here

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

HYDROPHOBIC MODIFICATION OF CHARGEABLE PIGMENT PARTICLES

The present invention relates to hydrophobic modification of chargeable pigment particles and non-polar suspensions of such pigment particles.

5 Stable suspensions of chargeable pigment particles are desirable in certain applications wherein the formation of images (permanent or latent) requires charging or discharging the pigment particles. Such applications include liquid toners, ink jet inks using solvents and electrostatic paints.

The preparation of such suspensions has been documented in literature. To stabilize hydrophilic pigments in non-polar solvents, steric barriers are introduced to provide stabilization.
10 Common strategies to do so include the use of ionic surfactants or polymeric dispersants which adsorb on the pigment (e.g., U.S. Patents 5,536,615 and 5,482,809); dendrimers (e.g., U.S. Patent 5,558,968) or non-polymeric resins (e.g., U.S. Patent 5,521,046) to modify the pigment surface. Though polymeric dyes (U.S. Patents 5,521,271 and 5,563,024) have been disclosed as alternatives to pigments for use in such applications, their inferior lightfastness and weatherability, coupled with
15 their relatively high production costs, have restricted their usage.

Stable suspensions of chargeable pigment particles in non-polar solvents is difficult to prepare, mainly for two reasons. First, many chargeable pigment particles contain surface polar functional groups like carboxylic acid. In addition to rendering the pigment chargeable, these polar functional groups also make the pigment hydrophilic. In non-polar systems containing non-polar
20 solvents, the hydrophilicity of the pigment particles causes them to be attracted to each other rather than to the non-polar solvent, resulting in flocculation and destabilization of the pigment suspension.

Second, in contrast to the possibility of applying both steric and electrostatic interactions to combat flocculation in polar systems, mainly steric interaction can be applied in non-polar systems. In most cases, surfactants are used to provide steric stabilization in suspending such particles. The
25 polar ends of the surfactants adsorb onto the hydrophilic pigment surface, and the hydrophobic portion is solvated by the non-polar solvent. This mode of weak attachment leads to flocculation and degradation of the non-polar suspension. A disadvantage of using physically adsorbed surfactants or dispersants in suspensions is that under external stress, like a high electric field, some of these suspensions or formulations become unstable. This is due to the dissociation or desorption
30 of a surfactant or resin from the pigment particle surface.

The use of dendrimers that are covalently bonded to pigment surfaces partially addresses the problem of desorption, but the process of assembling such a complex molecular architecture on the pigment surface translates into a lengthy preparation and high production cost.

A need therefore exists for a method of making a non-polar suspension of chargeable pigment particles that does not suffer from problems such as desorption, and is available as a lower cost alternative to the use of dendrimers and the like.

According to the present invention there is provided a method for making a non-polar
5 suspension of chargeable pigment particles comprising (1) forming a suspension of pigment particles in a non-polar solvent, wherein the pigment particles are inherently ionic or are chargeable and possess surface anchoring groups on the surface of the pigment particles; and (2) contacting the pigment particles with a polymeric resin comprising a hydrophobic region and a reactive group that reacts with the surface-anchoring groups on the surface of the pigment particle. The surface
10 anchoring group and the polymeric resin can form a covalent or hydrogen bonding, preferably a covalent bond. The polymeric resin preferably comprises a maleic anhydride group.

The present invention further provides a non-polar suspension of inherently ionic or chargeable pigment particles having surface-anchoring groups on the surface of the particles. The suspension comprises the pigment particles suspended in a non-polar solvent, wherein the pigment
15 particles have on their surface a polymeric resin that comprises a hydrophobic region and a reactive group that reacts with the surface-anchoring groups on the pigment surface.

The present invention further provides a method of hydrophobically modifying chargeable pigment particles having a first functional group, the method comprising contacting the pigment particles with a polymer having a hydrophobic region and a second functional group in such a way
20 as to form a covalent bond between the first and second functional groups.

The pigment particles for modification according to the present invention advantageously have two desirable properties: chargeability and susceptibility to being modified. Chargeability is imparted by the reactive or functional groups present on the pigment. Thus, chargeable pigments can be divided into two categories. The first category includes pigments that are inherently ionic in
25 character. Examples of this type of pigment include complexes of transitional metals, e.g., iron blue; and ionic compounds, e.g., calcium sulfate. Some pigments contain residual ionic species on their surface, as a result of an inefficient washing process. Although such pigments may be used in the present process, since the ionic species on the pigment surface are not bound tightly on the surface, they may be lost or washed off during the process steps, and hence chargeability of such pigments
30 may not be satisfactory and may vary from batch to batch.

The second category of chargeable pigments includes pigments that are not inherently ionic and yet possess chargeable groups on the surface. These groups include, but are not limited to, carboxylic groups, hydroxyl groups including phenolic hydroxyl groups, alkyl hydroxyl groups, and

alkenyl hydroxyl groups, amino groups which may be primary, secondary, tertiary or quaternary ammonium groups, quinoline groups, and other functional groups that contain heteroatoms such as nitrogen, oxygen, or sulfur. Examples of pigments possessing such groups include oxidized carbon black. A particularly suitable oxidized carbon black pigment is FXTM 200 supplied by Degussa Company (Ridgefield Park, NJ). Those of ordinary skill in the art know that oxidized carbon black contains carboxyl, hydroxyl, keto, aldehyde, and/or other chargeable groups. Other examples of pigments include Hansa Yellow, Dinitroaniline Orange, Naphthol Red, Red Lake C, Lithol Red, Rubine Red, Dianisidine Blue, Alizarin Lake, and Nickel Azo Yellow, which bear hydroxyl groups, and Disperse Yellow 9, Disperse Black 1, and Solvent Brown, which bear amino groups.

The second property desirable in a pigment is its susceptibility or reactivity to permit surface modification. Thus, the pigments should possess surface reactive groups such as, carboxylic groups, hydroxyl groups, amino groups, quinoline groups, thiol groups, epoxy groups, or dioxetane groups.

The polymeric resin used to modify the surface of the pigment preferably should meet two criteria. First, it should have a functional group that can react with the surface anchoring groups of the pigment. Such functional groups include hydroxy, carboxylic acid, carboxy anhydride, thiols, amino, amide, mono or di- substituted amide, isocyanide, isocyanate, and the like.

Second, the polymer should have a hydrophobic portion in its structure capable of being solvated by the non-polar solvent. This portion of the polymeric resin can be of any suitable structure, such as polyalkylenes, polyvinyl halides, polyacrylates, and polystyrenes. Certain specific examples include using polystyrene for being solvated by aromatic solvents (e.g., toluene) and polyethylene for being solvated by aliphatic solvents (e.g., Isopar E or cyclohexane).

Copolymers composed of a reactive polar monomer and a hydrophobic monomer are particularly useful as modifying polymeric resins. Examples of reactive polar monomers include maleic anhydride, acrylic acid, acrylamide, aldehyde containing monomers, amine or amide containing monomers, hydroxyalkyl acrylates, and epoxy containing monomers. Maleic anhydride is a preferred monomer. Examples of hydrophobic monomers include alkenes such as ethylene, propylene, and butylene, substituted alkenes such as styrene, acrylic esters, vinyl ethers, vinyl alkanes, and vinyl halides. Styrene is a preferred hydrophobic monomer.

The copolymers can be blocked, graft, random, statistical, or alternate. Block and graft copolymers are further preferred. Block copolymers can be di, tri, tetra, or multiblock. An example of a suitable block copolymer is polymaleic anhydride-*block*-polyethylene (Aldrich Chemical Co., Milwaukee, WI), which is useful, for example, for modifying and suspending carbon black in paraffinic solvents. The maleic anhydride functionality can react with the surface groups of the

carbon black, particularly the hydroxyl groups to form a covalent bond. The polyethylene portion provides suspendability in paraffinic solvents.

Other useful polymers include polystyrene-*block*-maleic anhydride; graft polymers such as polyethylene-*graft*-polymaleic anhydride; polycycloalkylethylene-*graft*-polymaleic anhydride, like
5 polycyclohexylethylene-*graft*-maleic anhydride; and polymaleic anhydride-*graft*-polyacrylate, like polymaleic anhydride-*graft*-polymethylacrylate.

It is particularly preferred that a covalent bond is formed between the reactive groups of the polymer resin and those of the pigment particles. The covalent bond formation can be confirmed by methods known to those of ordinary skill in the art, for example, by infrared spectroscopy. Thus,
10 for example, when a polymeric resin containing a maleic anhydride resin is used to modify the surface of a carbon black pigment, the formation of a covalent bond formation can be confirmed by the appearance of infrared absorption peaks corresponding to the ester carbonyl and carboxyl carbonyl and the disappearance of the carbonyl peaks due to the anhydride groups. Further, the polymer when it is covalently bound to a pigment would not be removed from the pigment by
15 repeated washing with a solvent for the free or unbound polymer. This lack of solubility of the bound polymer can be used as a means for confirming or identifying covalent bond formation.

To provide sufficient steric stabilization for the pigment to be suspended in the solvent, the polymer preferably has a molecular weight from about 15,000 to about 200,000, more desirably from about 15,000 to about 100,000. Even higher molecular weight polymers may be employed; however,
20 the amount of polymer needs to be controlled to avoid processing difficulties due to the high viscosities generally expected of high molecular weight polymers.

The quantity of polymer used would also depend upon factors such as the specific gravity and the surface area of the pigment. Usually the amount of polymer will be from about 1 to about 99 percent, and preferably ranges between about 30 and about 50 percent based on the weight of the
25 pigment.

The surface modification would to alter the density of the pigment. Thus, for example, the density of the modified pigment can be less than that of the pigment itself. This reduction in density is an advantage; it helps in stabilizing suspensions in non-polar solvents by bringing down the density of the pigment close to that of the solvent. Since the density of the surface modifying
30 polymer is generally less than that of heavy or high density pigments, such as titanium dioxide, heavy pigments tend to require more polymer, whereas light pigments, e.g., carbon black, may require a quantity of polymer closer to the low end of this range.

Examples of useful solvents include non-polar, aprotic solvents, such as saturated aliphatic

solvents, like Isopar G (Exxon Chemical Co., Houston, TX); saturated cyclic aliphatic solvents like decahydronaphthalene and cyclohexane (both from Aldrich Chemical Co.); mixtures of both aliphatic and cyclic aliphatic solvents like VMP Naphtha (Ashland Chemical Co., Chicago, IL); aromatic solvents like toluene or xylene (both from Aldrich Chemical Co.); and halogenated hydrocarbons like chloroform and dichloroethane (both from Aldrich Chemical Co.).

The preparation of the non-polar suspensions of the present invention involves the following steps: milling and surface modification. Milling may be performed by any known technique, including using a glass jar charged with glass beads, or a media mill. The usual milling medium of choice is glass beads. For most applications, glass beads of 2 mm diameter are sufficient. If a smaller particle size is desired, zirconium beads with a diameter less than 1 mm can be used. The particle size of the suspended particles can be monitored periodically to determine the desired milling time. Milling can be stopped when no more changes in the particle size occurs. Depending upon the hardness of the pigment, typical milling times range from about one hour to about two hours. The final particle size of the pigment particles is controlled by the size of the milling media and the time of milling. When the milling time is long enough, such as greater than about one hour, enough heat is usually generated to allow the reactive group of the polymeric resin to react with the anchoring group on the pigment surface. If the heat generated during milling is not sufficient to realize the desired amount of reaction, the polymer/pigment mixture can be heated. Heating can be provided by any known heating means.

After the above surface modification step is complete, if desired, the modified pigment particles may be recovered, as by filtration, and washed to separate the pigments particles from the suspension medium. Such modified pigment particles may be used as such or resuspended in another suitable non-polar vehicle.

The stability and chargeability of the pigment suspensions can be determined by any method known to those of ordinary skill in the art. A simple way to study suspension stability is by placing the suspension in a graduate cylinder and observing if a phase separation occurs. If the suspension is not stable, phase separation will occur, forming a supernatant layer which is depleted in pigment and leaving a pigment sediment at the bottom of the container. The volumes or the heights of the supernatant and the sediment can be measured. By this method, one can compare the relative stability of pigment suspensions by (1) observing whether phase separation occurs or not; and (2) comparing the time for the phase separation to happen.

Another method of measuring suspension stability involves the use of an instrument which provides a quantitative measure of the sedimentation rate, e.g., a BYK Chemie Dynometer Type 191

0 (Silver Spring, MD). This method involves measuring the weight of the sediment phase separating out over a given period of time on a sedimentation disk positioned within the suspension with its concave surface facing upwards. A stable suspension would have a sedimentation rate of less than about 15 mg per hour, preferably close to zero mg per hour.

5 The chargeability or the ability of the pigment suspension to respond to an external electric field can be determined as follows.

When a pigment suspension in a microtubule is put into a parallel, pulsating electric field, the pigment particles, which are chargeable, will migrate from one end of the electrode to the other. The direction of migration of particles depends upon their net surface charge and the polarities of the electrodes. The synchronized movement of the particles will generate an impression that the whole microtubule is vibrating periodically between the two electrodes. The minimum potential difference, or minimum voltage, across the electrodes needed to cause the particles to migrate would be inversely proportional to the charges induced on or carried by the individual pigment particle. Pigment particles that are highly charged or are easily chargeable would require a lower minimum voltage to migrate. Consequently, when compared among a series of samples, the minimum or threshold voltage to cause such changes will give the relative chargeability or surface charges of the pigment particles.

The minimum voltage can be measured by methods known to those of ordinary skill in the art. Thus, a solution of a non-polar suspension is placed in a microtubule, such as the one available from Viprocom Co. in Mountain Lake, NJ. The microtubule is then placed between two parallel copper electrodes mounted on an acrylic plate. The whole set-up is then placed under a microscope. A pulsating voltage with a square wave form is applied across the electrode and changes in the appearance of the tube are noted. The minimum voltage that causes migration of the particles is also noted. A similar method is described in Y. Hirobe et al., IS&T's Eighth Int'l Congress on Advances in Non-Impact Printing Technologies, page 198 (1992).

25 The present invention will be further described by the following non-limiting illustrative examples.

EXAMPLE 1

30 This Example illustrates a method of modifying oxidized carbon black using a poly(styrene-co-maleic anhydride) and a method of preparing a non-polar suspension of the modified oxidized carbon black.

0.45 gram of poly(styrene-co-maleic anhydride) (MW 200,000, Aldrich Catalog No.

42694-6) was first dissolved in 48.5 grams of toluene in an 8 ounce glass jar with a screw cap. 1.5 grams of oxidized carbon black (Cabot Corporation, Billerica, MA) and 90 grams of glass beads (2 mm diameter) were added to the solution. The container was closed tightly and shaken using a RED DEVIL™ 5400 Paint Mixer (Red Devil Co., Minneapolis, MN). The particle size was monitored periodically using a Nicomp Particle Size Analyzer Model 370 (Nicomp, Santa Barbara, CA). The milling was stopped when no further change in particle size was observed to obtain a suspension containing the modified pigment. The suspension was suitable to be used as such or suitably diluted with a non-polar solvent to obtain a more dilute suspension.

EXAMPLE 2

This Example illustrates a method of modifying oxidized carbon black using a polyethylene-graft-maleic anhydride polymer and a method of preparing a non-polar suspension of the modified pigment.

The procedure in Example 1 was followed except that a polyethylene-graft-maleic anhydride (Aldrich Catalog No. 44240-2) was used as the modifying polymer. Decahydronaphthalene (Koch Chemical, Corpus Christi, TX) was used as the non-polar solvent. A modified pigment and a non-polar suspension were obtained.

EXAMPLE 3

This Example illustrates an advantage of using a high molecular weight polymeric resin to modify oxidized carbon black. Thus, for comparative purposes, modification was carried out using a poly(styrene-co-maleic anhydride) of a molecular weight lower than that of the polymer employed in Example 1.

The procedure of Example 1 was followed but poly(styrene-co-maleic anhydride) of molecular weight 1,900 (Aldrich Catalog No. 42650-4) was employed instead of the polymer of MW 200,000, and a modified pigment was obtained. The sedimentation rate of a non-polar suspension was measured as follows. The amount of the sediment formed was recorded as a function of time using a BYK Chemie Dynometer Type 191 0 (Silver Spring, MD). The rate was determined by dividing the amount of sediment collected by the elapsed time. The accuracy of measurement is +/- 1.0 mg per hour. The sedimentation rates of non-polar suspensions prepared as illustrated in Examples 1 and 3 were measured and the results obtained are set forth in Table 1.

Table 1. Sedimentation rates of non-polar suspensions of Examples 1 and 3.

<u>Example</u>	<u>Molecular weight of polymer</u>	<u>Sedimentation rate (mg/hr)</u>
----------------	--	-----------------------------------

5

Example 1	200,000	1.5
Example 3	1,900	72.3

10 The foregoing shows that the higher molecular weight polymer is superior in stabilizing the pigment suspension to the lower molecular weight polymer.

EXAMPLE 4

15 This Example illustrates the suitability of the modified pigments of the present invention for preparing stable non-polar suspensions in several non-polar solvents.

Non-polar suspensions were prepared using the modified pigment of Example 1 in cyclohexane, toluene, and VMP naphtha. The suspensions contained 3% by weight of carbon black, 0.9% by weight of polymeric resin, and the balance was the non-polar solvent. The sedimentation rates of the suspensions were measured as illustrated in Example 3 and the results obtained are set
20 forth in Table 2.

Table 2. Sedimentation rates in various solvents.

<u>Pigment used</u>	<u>Solvent</u>	<u>Sedimentation rate (mg/hr)</u>
---------------------	----------------	-----------------------------------

25 Carbon Black	Cyclohexane	0
Carbon Black	Toluene	1.5
Carbon Black	VMP Naphtha	3.3

30 The observed sedimentation rates were well below the practical limiting rate for stable suspensions (15 mg/hr). The foregoing shows that the modified pigment of the present invention is suitable for preparing stable non-polar suspensions in several non-polar solvents.

EXAMPLE 5

This Example illustrates a method of evaluating the chargeability of the modified pigments of the present invention.

Two copper strips, each with dimensions of 1 cm x 5 cm x 0.012 cm, were mounted end to end onto an acrylic plate. The gap between the ends of the strips was about 120 microns. The copper strip ends away from the gap were connected to a power supply with a Model 7500 amplifier (Krohn-hite, Avon, MA) and a function generator (Model 95, Wavetek, San Diego, CA).

A pigment suspension prepared from the modified carbon black in Example 2 in decahydronaphthalene was placed in a Viprocom microtubule which was later placed in the gap between the copper strips. The whole assembly was then placed on the sample stage of a microscope. The function generator delivered a pulsating electric field across the gap. As the pulse sequence was initiated, any change in appearance of the contents of the microtubule was noted. The voltage was increased slowly until a "vibrating motion" was observed in the microtubule. The minimum voltage needed to effect such a change was recorded. It was observed that the pigment was chargeable as shown the vibrating motion of the contents of the microtubule at the minimum voltage. The experiment was repeated with non-polar suspensions containing the pigment of Example 2 in toluene or VMP naphtha, and the minimum voltage to cause a vibrating motion of the microtubule was noted. The results obtained are set forth in Table 3.

Table 3. Minimum voltage required to cause visual changes in the tube containing the pigment suspension

<u>Pigment used</u>	<u>Solvent</u>	<u>Minimum voltage (V)</u>
Carbon Black	Decahydronaphthalene	40
Carbon Black	Toluene	45
Carbon Black	VMP Naptha	>75

The foregoing shows that the modified pigment of the present invention is chargeable. The foregoing further shows that the chargeability of the pigments can be influenced by the suspension medium. The modified pigments were more chargeable in a higher dielectric medium (toluene or decahydronaphthalene) than in a lower dielectric medium (VMP naphtha).

EXAMPLE 6

This Example illustrates another advantage of the surface modification of the present

invention. A polymer that forms a covalent bond with a pigment is superior in modifying the pigment and in providing a stable non-polar suspension compared to a polymer that physically adsorbs and does not form a covalent bond with the pigment.

A suspension of oxidized carbon black was prepared as in Example 1 except that the poly(styrene-*co*-maleic anhydride) was replaced by a commonly used modifier, SOLOSPERSE™ 17940 (Zeneca, Wilmington, DE). This modifier is believed to be a block copolymer of polymeric fatty ester containing proprietary anchoring groups with one end of the polymer capable of being adsorbed physically onto the pigment and the other end capable of being solvated by the non-polar solvent. The stability of this suspension was compared with that of the non-polar suspension of Example 1. The sedimentation rates were measured and the results obtained are set forth in Table 4.

Table 4. Stabilities of the suspensions of Examples 1 and 6

<u>Suspension</u>	<u>Phase separation observed</u>	<u>Minutes to phase separate</u>	<u>Sedimentation rate (mg/hr)</u>
Example 1	No	---	0
Example 6	Yes	10	1,830

The foregoing shows that a pigment modified with a polymer that formed a covalent bond with the pigment forms a more stable suspension compared to a pigment modified by a polymer that physically adsorbs on the polymer.

EXAMPLE 7

This Example illustrates the stability of the modification when a covalent bond is formed between the pigment and the modifying polymer.

A polyethylene-*graft*-maleic anhydride was used to modify oxidized carbon black as illustrated in Example 2. The modified pigment was separated from the solvent by filtration and the filtered pigment was washed with decahydronaphthalene 16 times. The washed pigment formed a stable suspension in a non-polar solvent, thereby confirming that the polymer was not removed by the washing.

CLAIMS:

1. A method of hydrophobically modifying chargeable pigment particles having a first functional group, said method comprising contacting said pigment particles with a polymer having a hydrophobic region and a second functional group so as to form a covalent bond between said first
5 and second functional groups.
2. A method according to claim 1, wherein said contacting is carried out in a non-polar solvent.
- 10 3. A method according to claim 1 or claim 2, wherein said contacting is carried out with milling.
4. A method according to claim 1 or claim 2 or claim 3, wherein said first functional group is selected from the group consisting of carboxyl, hydroxyl e.g. a phenolic hydroxyl, anhydrido, amino, amido, halo, thiol, epoxy, keto, aldehydo, isocyanato, and alkenyl.
15
5. A method according to any one of the preceding claims, wherein said second functional group is selected from the group consisting of carboxyl, hydroxyl, anhydrido, amino, amido, halo, thiol, epoxy, keto, aldehydo, isocyanato, and alkenyl.
20
6. A method according to any one of the preceding claims, wherein said polymer is a block or graft copolymer.
7. A method according to claim 6, wherein the hydrophobic region of the copolymer is
25 composed of an alkene or substituted alkene monomer.
8. A method according to claim 6 or claim 7, wherein said copolymer is selected from the group consisting of poly(ethylene-co-maleic anhydride), poly(styrene-co-maleic anhydride), poly(cycloalkylethylene-co-maleic anhydride), and poly(maleic anhydride-co-acrylate).
30
9. A method according to claim 6 or claim 7, wherein said copolymer is poly(ethylene-graft-maleic anhydride).

10. A method according to any one of the preceding claims, wherein said pigment is oxidized carbon black.

11. A hydrophobic modified pigment prepared by a method according to any one of the
5 preceding claims.

12. A non-polar suspension comprising hydrophobically modified chargeable pigment particles prepared by a method according to any one of claims 1 to 10.

10 13. A method for making a non-polar suspension of chargeable pigment particles comprising: (1) forming a suspension of pigment particles in a non-polar solvent, wherein the pigment particles are inherently ionic or chargeable and possess surface anchoring groups on the surface of the pigment particles; and (2) contacting the suspension of pigment particles with a polymeric resin comprising a hydrophobic region and a maleic anhydride group.

15 14. A method according to claim 13, wherein said pigment is oxidized carbon black.

15. A method according to claim 13 or claim 14, wherein said polymeric resin is a block or graft copolymer of maleic anhydride and a hydrophobic monomer selected from the group
20 consisting of ethylene, methyl acrylate, cycloalkylethylene, and styrene.

16. A non-polar suspension of inherently ionic or chargeable pigment particles having surface-anchoring groups on the surface of said particles comprising said pigment particles suspended in a non-polar solvent, wherein said pigment particles have on their surface a polymeric
25 resin that comprises a hydrophobic region and a maleic anhydride group that reacts with the surface-anchoring groups on the pigment surface.

17. A non-polar suspension according to claim 16, wherein said pigment is oxidized carbon black.

30 18. A non-polar suspension according to claim 16 or claim 17, wherein said polymeric resin is a block or graft copolymer of maleic anhydride and a hydrophobic monomer selected from the group consisting of ethylene, methyl acrylate, cycloalkylethylene, and styrene.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/02378

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09C3/10 C09C1/56

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 787 777 A (NIPPON CATALYTIC CHEM IND) 6 August 1997 (1997-08-06) the whole document ---	1-18
X	WO 87 05924 A (REVERTEX LTD) 8 October 1987 (1987-10-08) the whole document ---	1-18
X	GB 1 514 922 A (ICI LTD) 21 June 1978 (1978-06-21) the whole document -----	1-9



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

28 October 1999

Date of mailing of the international search report

05/11/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

LIBBERECHT, E

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/02378

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0787777 A	06-08-1997	JP 8337737 A	24-12-1996
		JP 9003356 A	07-01-1997
		JP 9059331 A	04-03-1997
		JP 9309904 A	02-12-1997
		WO 9700295 A	03-01-1997
		US 5952429 A	14-09-1999
		JP 9272706 A	21-10-1997
		JP 9272831 A	21-10-1997
WO 8705924 A	08-10-1987	AU 7210087 A	20-10-1987
		EP 0261220 A	30-03-1988
GB 1514922 A	21-06-1978	AU 8225675 A	23-12-1976
		DE 2527284 A	08-01-1976
		FR 2275486 A	16-01-1976
		IT 1039099 B	10-12-1979
		JP 51013843 A	03-02-1976
		NL 7507307 A	23-12-1975
		NZ 177833 A	02-06-1978